

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



00 DEC 2004


(43) International Publication Date
22 January 2004 (22.01.2004)

PCT

(10) International Publication Number
WO 2004/007166 A1

- (51) International Patent Classification⁷: B29C 33/42, 33/40, H01J 9/24
- (74) Agents: PECHMAN, Robert J., et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).
- (21) International Application Number:
PCT/US2003/018232
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 10 June 2003 (10.06.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2002-201539 10 July 2002 (10.07.2002) JP
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): YOKOYAMA, Chikafumi [JP/JP]; 6-25-30, Minami-Kurihara, Zama, Kanagawa 225-0015 (JP). YODA, Akira [JP/JP]; 9-19, Ogawa 3-chome, Machida, Tokyo 194-0003 (JP). KIKUCHI, Hiroshi [JP/JP]; 7-3-1, Tsukimino, Yamato, Kanagawa 242-0002 (JP).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FLEXIBLE MOLD AND METHOD OF MANUFACTURING MICROSTRUCTURE USING THE SAME



(57) **Abstract:** To provide a flexible mold (10) useful for manufacturing a PDP rib having a lattice pattern and other microstructures, and capable of highly precisely manufacturing the microstructures without involving defects such as occurrence of bubbles and pattern deformation. A flexible mold (10) comprises a base layer (2) made of a first curable material having a viscosity of 3,000 to 100,000 cps at 10 to 80°C and a coating layer (3) coating a surface of the base layer (2) and made of a second curable material having a viscosity of 200 cps or below at 10 to 80°C.

WO 2004/007166 A1